



#### MADE IN INDIA

# Mixed Bed Resin 300

#### **Description:**

ASHAION MB 300 is a mixed bed ion exchange resin. It is a mixture of highly purified and super regenerated strong acid cation and strong base onion resins in 1: 2 stoichiometrically equivalent volume ratio of cation in H form and anion in OH form

### **Application:**

ASHAION MB 300 is recommended in any non regenerable mixed bed application where reliable production of the highest quality water is required and where "as supplied" resin must have an absolute minimum of ionic and nonionic contamination.

| Characteristics:                            |                         |   |                         |
|---|-------------------------|---|-------------------------|
| Physical                                    |                         |   |                         |
| Physical form                               |                         | Spherical beads                                 |                         |
| Shipping weight                             |                         | 690 - 730 kg/m3, approximately                  |                         |
| Particle size range<br>> 1.2 mm<br>< 0.3 mm |                         | 0.3 to 1.2 mm<br>5.0%, maximum<br>1.0%, maximum |                         |
| Uniformity co-efficient                     |                         | 1.7, maximum                                    |                         |
| Effective size                              |                         | 0.45 to 0.65 mm                                 |                         |
| Microscopic examination                     |                         | Surface cracks not more than 5%.                |                         |
| Chemical                                    | Cation Resin            |   | Anion Resin             |
| Matrix                                      | Crosslinked polystyrene |   | Crosslinked polystyrene |
| Туре  | Gel                     |   | Gel                     |
| Functional group                            | Sulphonic acid          |   | Quaternary ammonium     |
| Total exchange capacity                     | 1.9 meq/ml              |   | 1.0 meq/ml              |
| lonic conversion                            | 99%, minimum H+         |   | 90%, minimum OH-        |
| Moisture holding capacity                   | 49 - 55%                |   | 48-58% (in Cl form)     |

## Packing

HDPE lined bags Supersack 25/50 Its 1000 Itrs

#### Storage

lon exchange resins require proper care at all times. Resins must never be allowed to become dry. Resins should therefore be always kept in the shade. Since ASHAION MB 300 is supplied in highly regenerated condition, any exposure to atmospheric air must be avoided as this will convert it to the carbonate form. The resin packing should not be opened during storage.

#### Safety

Acid and alkali solutions are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.