



# Cation Exchange Resin C 250 Na

## Description:

**ASHAION® C 250 Na** is a high-capacity, strongly acidic cation exchange resin in bead form, derived from crosslinked polystyrene with a gel structure. It contains sulfonic acid functional groups and is supplied in the sodium form in a moist condition. Designed for high-efficiency water softening, it offers excellent operational capacity, durability, and long service life across a wide range of industrial and commercial applications.

## Application:

**ASHAION® C 250 Na** is widely used in the sodium form for water softening applications in industrial and commercial systems. It can also be utilized in two-stage deionization processes as the cation exchanger in the hydrogen cycle after appropriate regeneration, ensuring flexibility across various water treatment setups.

## Characteristics:

Appearance	Translucent golden yellow beads
Matrix	Styrene divinylbenzene copolymer
Functional Group	Sulphonic Acid
Ionic form as supplied	Sodium (Na <sup>+</sup> )
Total exchange capacity	2.0 meq/ml, minimum
Moisture holding capacity	43 - 50 %
Shipping weight *	800-820
Bead strength	300 g/bead, average
Particle size range	0.3 to 1.2 mm
> 1.2 mm	5.0 %, maximum
< 0.3 mm	1.0 %, maximum
Uniformity co-efficient	1.7, maximum
Effective size	0.45 to 0.55 mm
Maximum operating temperature	140° C
Volume Change	Na to H, 6 - 9%
Operating pH range	0 to 14
Resistance to reducing agents	Good
Resistance to oxidizing agents	Generally good, chlorine should be absent
Osmotic Stability	Excellent



## Cation Exchange Resin C 250 Na

### Packing:

HDPE Lined bags : 25/50 Its

LDPE bags : 1 cft/25 Its

Super sack : 1000 Its

Super sack : 35/40/42 cft

MS/HDPE drums with liner bags : 180/200 Its

Fiber drums with liner bags : 7 cft

### Storage:

Ion exchange resins require consistent care to maintain their effectiveness. It is essential to prevent the resin from drying out.

During storage, regularly inspect the resin by opening the plastic bags and checking its condition. If the resin appears dry, add sufficient clean demineralized water to keep it fully moist at all times.

### Safety:

Acid and alkali solutions used for regeneration are corrosive and must be handled carefully to prevent contact with the eyes and skin. When using any oxidizing agents, appropriate safety precautions should be taken to prevent accidents and protect the resin from potential damage.

The **ASHAION®** range of ion exchange resins is manufactured at state-of-the-art, ISO 9001 and ISO 14001 certified facilities located in Maharashtra, India. To the best of our knowledge, the information provided in this publication is accurate. Asha Resins Limited follows a policy of continuous improvement and reserves the right to modify the information provided herein without prior notice.

**ASHAION®** is a registered trademark of Asha Resins Limited.